

# Extending Our Understanding of Compliant Thermal Barrier Performance



**Jeffrey J. DeMange**  
*The University of Toledo*

**Joshua R. Finkbeiner, Patrick H. Dunlap**  
*NASA Glenn Research Center*

**Materials Science & Technology**  
**Thermal Protection Materials and Systems**  
**Pittsburgh, PA**  
**October 12-16, 2014**

This research was funded by the U.S. Government under NASA Contract NNC13BA10B. The views and conclusions contained in this document are those of the authors and should not be interpreted as representing the official policies, either expressed or implied, of the U.S. Government.

# Content of Discussion

- Introduction
  - Compliant Thermal Barriers (CTB) - What are they? Where are they used?
  - Treatment of CTB's – How are they implemented?
  - Construction, requirements, and characteristics of thermal barriers
- Current Efforts to Improve Understanding
  - Thermal
    - What we know
    - Modeling efforts
    - Case Study: Effect of core density on flow/leakage
  - Mechanical
    - What we know
    - Modeling efforts
    - Case Study: Effect of core density on loads
- Still more to do
- Summary

# INTRODUCTION

# An Integral Part of the TPS



**Compliant Thermal Barriers**

- Often referred to as “thermal seals” or “seals”
- One “class” of thermal barriers
- High-temp. ceramic-based fibrous materials
- Installed in TPS interface gaps
- Roles
  - Thermal – limit inboard temperatures
  - Structural – accommodate deflections
- Multitude of configurations...but share common elements



**Vehicle Penetrations**




**Doors**




**Control Surfaces**

# Compliant Thermal Barrier Construction




**Blanket Thermal Barrier (BTB)**



**Hybrid Thermal Barrier (HTB)**

- Outer sheath
  - 1+ layers of aluminosilicate woven fabric (e.g., Nextel™)
  - Coatings: RTV, emissivity, etc.
- Core
  - Aluminosilicate blanket (e.g., Saffil)
  - Metallic spring tube
- Other
  - Stitching to control shape/size and keep insulation in tact
  - End treatments/closeouts





# Compliant Thermal Barrier Requirements & Characteristics

- General Requirements
  - Survive in harsh environments (thermally, chemically, tribologically)
  - Mitigate heat transfer
    - Good thermal insulators
    - Minimize convective flow (in combination with inboard environmental barriers)
    - Mitigate radiation heat transfer
  - Exhibit flexibility/conformability
  - Remain resilient
  - Meet load requirements
- Characteristics
  - Made of high temperature ceramic fiber-based materials
  - Utilize high-performance insulation
  - Permeable
  - Compliant
  - Exhibit set/compaction (even at ambient temperatures)
  - Non-linear hysteretic loading behavior

# General Perception vs. Reality

## More Art than Science???

- Typically considered as “gap fillers” to fill a space – design it to fit
- Often an “after-thought” in design of TPS
- Minimal effort to optimize design → need guidance
  - Thermally: How much insulation is needed? Is there an optimal orientation?
  - Mechanically: Are there load requirements for the interface? What level of durability does the barrier need? What kind of gap change does it need to accommodate?
- Strong reliance on heritage use

## The Case for More Science

- Case studies
  - Door closure forces – Space Shuttle
  - Panel installation – MPCV
  - Potential tile debonding – MPCV


# **THE SCIENCE: CURRENT EFFORTS TO IMPROVE UNDERSTANDING OF THERMAL BEHAVIOR**




# Thermal Behavior: What We Know

- Heat transfer occurs via several mechanisms
  - Conduction (solid and gas)
  - Convection (natural? and forced)
  - Radiation
- Insulation density/pore size affect degree and modes of heat transfer
- Different modes are active/dominant under different conditions
  - Temperature (e.g., radiation dominant at high temperatures)
  - Pressure (e.g., gas conduction greater at higher pressures)

**∴ Heat transfer in porous soft good TPS is a complex interplay of mechanisms affected by many variables!**



(Gibson & Ashby, 1997)



(Daryabeigi *et al.*, 2010)

# Energy Equation for Porous Media

- Generalized heat transfer equation

$$(\rho c_p)_g \left[ \frac{(\rho c)_s}{(\rho c_p)_g} \frac{\partial T}{\partial t} + \vec{u} \cdot \nabla T \right] = \nabla \cdot (k_e \nabla T) + \dot{q}''' + \frac{\mu}{K} \vec{u}^2$$

Thermal Inertia      Convection      Conduction + Radiation      Heat Generation      Viscous dissipation

Darcy Velocity:  $\vec{u} = \frac{\dot{m}}{\rho_g} = \phi u_p$


- Heat transfer coefficients (Daryabeigi *et al.*, 2010)

$$k_e = \underbrace{k_s + k_g}_{\text{Conduction}} + \underbrace{k_r}_{\text{Radiation}}$$


$$k_s(T) = F_s f_v^b k_s^*(T) \qquad k_g(T, P) = \frac{k_{g0}(T)}{\Phi + 2\Psi \frac{\beta}{Pr} Kn}$$

$$k_r = \frac{16\sigma n^{*2} T^3}{3\rho e}$$

# Case Study: Effect of Core Density on Flow



(DeMange, unpublished)



(Shuo *et al.*, 2011)

$$-\nabla P = \frac{\mu}{K} \vec{u} + \rho C |\vec{u}| \vec{u}$$

(Stanek & Szekely, 1974)

$$\frac{(P_1^2 - P_0^2)A}{2\dot{m}\mu RTL} = \frac{1}{K} + C \frac{\dot{m}}{A\mu}$$



# **THE SCIENCE: CURRENT EFFORTS TO IMPROVE UNDERSTANDING OF MECHANICAL BEHAVIOR**

# Mechanical Behavior: What We Know

- Similar behavior to low-density porous foam materials
  - Linear elasticity (cell wall bending) → fiber bending
  - Plateau (cell wall buckling) → fiber breakage?
  - Densification (cell collapse) → pore collapse
- Strong effect of core density on mechanical performance (opposite to effect on insulating properties)

$$\sigma \propto \left( \frac{\rho^*}{\rho_s} \right)^n$$

- Exhibit hysteresis during loading, unloading
- Display compaction/set (even at RT) that decreases with number of cycles



# Modeling Efforts

- Van Wyk modeled compressibility of fibrous wool (1946)
  - Fiber as straight rod supported horizontally between 2 other rods
  - Many other studies based off Van Wyk's model
    - Komori, *et al.* (1977, 1992) – Orientation of fibers, fiber crimp
    - Beil, *et al.* (2002) – Friction of fibers
    - Barbier, *et al.* (2009) – Hysteresis and friction

$$p = \frac{kEm^3}{\rho^3} \left( \frac{1}{v_i^3} - \frac{1}{v_o^3} \right) = kE(SVF_i^3 - SVF_o^3)$$

$p$  = contact load  
 $k$  = empirically determined constant (structure of fiber mass)  
 $E$  = Young's modulus of fibers  
 $m$  = mass of fibers  
 $\rho$  = density of fiber  
 $v_i$  = instantaneous bulk volume  
 $v_o$  = initial bulk volume  
 $SVF_i$  = instantaneous solid vol. fraction (volume fibers/bulk volume)  
 $SVF_o$  = initial solid vol. fraction (volume fibers/bulk volume)


- Pineda (2014) modeled Saffil insulation using energy method

$$U_{4P} = C_{10}(\bar{I}_1 - 3) + C_{20}(\bar{I}_1 - 3)^2 + C_{30}(\bar{I}_1 - 3)^3 + C_{40}(\bar{I}_1 - 3)^4 \frac{K}{2} (\ln J)^2$$

$$\mathbf{T} = \frac{2}{J} \left[ \left( \frac{\partial U}{\partial \bar{I}_1} + \bar{I}_1 \frac{\partial U}{\partial \bar{I}_2} \right) \bar{\mathbf{B}}' - \right] \frac{\partial U}{\partial \bar{I}_2} \bar{\mathbf{B}}'^2 + \frac{\partial U}{\partial J} \mathbf{1}$$




# Case Study: Effect of As-Fabricated Core Density on Loads




- Load behavior is highly nonlinear
- Nonlinear increase in peak load vs. as-fabricated density

# Case Study: Initial Modeling Efforts



Van Wyk Model



Pineda Model

- Van Wyk provides a reasonable first approximation of behavior of CTB's
- Pineda model matches Saffil performance well
- Models need expansion and refinement to incorporate effects from various sources

# Still so much to do...

- Heat transfer modeling
  - Need more data
    - Insulation – Effect of orientation (e.g., Saffil mat is transversely isotropic), other types (e.g., OFI, MLI, aerogels), how to reliably measure density
    - Effect of size/configuration – Hard to measure thermal properties on small samples
    - Variation between samples
  - Validation of models – How do we validate with combined conduction, convection, and radiation?
- Mechanical modeling
  - Need more data
    - Insulation – Basic mechanical material properties, effect of orientation (e.g., Saffil mat is transversely isotropic), other types (e.g., OFI, MLI, aerogels), how to reliably measure density
    - Effect of size/configuration (e.g., inclusion of spring tube, stitching, coatings)
    - Variation in samples
    - Effect of environment (temperature, pressure, space)
  - What's the best model?

**Goal: Develop a thermal barrier thermo-mechanical design/sizing tool**

# Summary

- Thermal barriers are integral to successful TPS performance
  - Considered more art, but need more science
  - Vehicle designers need guidance in designing, implementing, and maintaining thermal barriers
- Behavior of thermal barriers
  - Thermal performance
    - Heat transfer in porous soft goods is complex
    - Good baseline understanding of heat transfer in porous TPS
    - Challenges remain in characterization (e.g., lack of data, difficulty in testing small samples)
  - Mechanical performance
    - Less studied and understood
    - Very few models exist
    - Multitude of configurations and implementations creates modeling challenges
- Still much to do

# Points of Contact

---

Jeff DeMange

[jeffrey.j.demange@nasa.gov](mailto:jeffrey.j.demange@nasa.gov)

Pat Dunlap

[patrick.h.dunlap@nasa.gov](mailto:patrick.h.dunlap@nasa.gov)

Josh Finkbeiner

[joshua.r.finkbeiner@nasa.gov](mailto:joshua.r.finkbeiner@nasa.gov)

# Acknowledgements

---

- Evan Pineda – NASA GRC



# References

Daryabeigi, K., *et. al.*, “Combined Heat Transfer in High-Porosity High-Temperature Fibrous Insulations: Theory and Experimental Validation,” *Proceedings of the 10th AIAA/ASME Joint Thermophysics and Heat Transfer Conference*, No. AIAA 2010-4660, Chicago, IL, 28 June – 1 July, 2010.

Gibson, L. J. and Ashby, M. F., *Cellular Solids - Structures and Properties*, 2nd Ed., Cambridge University Press, Cambridge, UK, 1997.


Narasimhan, A., *Essentials of Heat and Fluid Flow in Porous Media*, CRC Press, Boca Raton, FL, 2013.

Shou, D., Fan, J., and Ding, F., “Hydraulic permeability of fibrous porous media,” *International Journal of Heat and Mass Transfer*, Vol. 54, 2011, 4009-4018.


Van Wyk, C. M., “Note on the Compressibility of Wool,” *Journal of the Textile Institute*, Vol. 37, 1946, T285-T292.

# Appendix

# Comparison to Van Wyk Model




569 (HS-to-BS)



570 (PtoP)


- Variability in compression performance of samples evident
- Suggest  $k$  varies from sample to sample (Van Wyk, 1946)
- Initial nonlinearity may be due to fiber slippage (Dunlop, 1974)

# Variation of k for Samples



- $k$  is function of initial density of core fibers (Dunlop, 1974)
- $k$  is complex function of fiber configuration (e.g., layer orientation)

# Effect of Insulation Density on Effective Thermal Conductivity



(Daryabeigi *et al.*, 2010)